

# Technical Information

---

## Technomelt Q 299M

<b>TYPE</b>	: Hot Melt
<b>PHYSICAL PROPERTIES</b>	: Appearance : Pigment White Viscosity : 4480 - 6720 cps @180°C 5680 - 8520 cps @170°C 7520 - 11280 cps @160°C Softening Point : 92 +/- 4°C Form : Chip or Granules Storage Life : 12 months
<b>OPERATING CONDITIONS</b>	: Can be used in all standard roller, wheel and nozzle applicators. Running Temperature : 160 - 180°C Setting Speed : Medium Open time : Medium
<b>SUGGESTED USES</b>	: Perfect Bookbinding It also conforms to composition requirements of FDA regulation 21 CFR 175.105 “ Adhesives”.
<b>PRECAUTIONS</b>	: Material is applied hot.Appropriate clothing and gloves should be used. Keep containers and premelters covered to avoid contamination. Rotate stock -first in- first out
<b>PACKAGE</b>	: 25 Kg/HDPE Bag

### **Henkel CAC Pvt. Ltd.**

*Plot No. 1/1 Part 2, TTC Indl. Area, Thane Belapur Road,  
Koparkhairne, Navi Mumbai- 400710  
Tel: +91-22- 27787371 Fax: +91-22-27780025*

